

POLYVINYL BUTYRAL RESINS

Product Code	Type	Form	% Non Volatiles	Viscosity		% Polyvinyl Butyral	% Polyvinyl Alcohol	% Polyvinyl Acetate	Softening Point °C	Notes
				Ref.	Unit					
SYNPOL B 30	Polyvinyl Butyral	Clear, Water white free flowing granules	> = 96			76 - 81	15 - 20	1 - 3	45 - 85	Wash primers, metal and foil coatings, wood finishes and knot sealers, Thermosetting and hot melt adhesives. Textile coatings, paper coatings, printing inks.
				V1	200 - 450					
				V2	50 - 100					
SYNPOL B 60	Polyvinyl Butyral	Clear, Water white free flowing granules	> = 96			76 - 81	15 - 20	1 - 3	51 - 55	
				V1	600 - 1200					
				V2	160 - 200					
SYNPOL B - 30 (15% in IPA)	Polyvinyl Butyral	15% solution of Synpol B 30 in Isopropyl Alcohol	15 ± 2	V3	3 - 6	
SYNPOL B - 60 (15% in IPA)	Polyvinyl Butyral	15% solution of Synpol B 60 in Isopropyl Alcohol	15 ± 2	V3	35 - 80	

Note:-

V1 of 15% solution in 60:40 Toluene/Ethanol (by weight) in Cps. at 25°C.

V2 of 10% solution in 95° Ethanol in Cps. at 25°C.

V3 of 15% solution in Iso Propyl Alcohol in Poises at 25°C.